

SPECIFICATION CHART OF TUBES AND PIPES																
CHEMICAL COMPOSITION													MECHANICAL PROPERTIES			
CS :- Carbon Steel													AS :- Alloy Steel			
SPECIFICATION	TYPE	C %	Mn%	P % MAX	S% MAX	Si %	Cr %	Cu % MAX	Mo % MAX	Ni % MAX	Va&	YIELD STRESS MPa	TENSILE STRENGTH MPa	ELONGATION IN 50mmMIN Longitudinal	IMPACT TEST -50°1 40x10	
STANDARD SPECIFICATION OF CARBON STEEL SEAMLESS TUBES / PIPES FOR HEAT EXCHANGER AND CONDENSER																
ASTM A179	CS	0.06-0.18	0.27-0.63	0.035	0.035	-	-	-	-	-	-	180MIN	325MIN	35.0	-	
STANDARD SPECIFICATION OF CARBON STEEL SEAMLESS BOILER TUBES/PIPES FOR HIGH PRESSURE SERVICES																
ASTM A192	CS	0.06-0.18	0.27-0.63	0.035	0.035	0.25MAX	-	-	-	-	-	180MIN	325MIN	35.0	-	
STANDARD SPECIFICATION OF CARBON STEEL SEAMLESS TUBES/PIPES FOR HIGH TEMPERATURE SERVICES																
1	ASTM A53/A	CS	0.25MAX	0.95MAX	0.050	0.060	-	-	-	-	-	205MIN	330MIN	36.0	-	
2	ASTM A53/B		0.30MAX	1.20MAX	0.050	0.060	-	-	-	-	-	240MIN	415MIN	29.5	-	
3	ASTM A106/A	CS	0.25MAX	0.27-0.93	0.035	0.035	0.10MIN	0.40MAX	0.40	0.15MAX	0.40	0.080	205MIN	330MIN	35.0	-
4	ASTM A106/B		0.30MAX	0.29-1.06	0.035	0.035	0.10MIN	0.40MAX	0.40	0.15MAX	0.40	0.080	240MIN	415MIN	30.0	-
5	ASTM A106/C		0.35MAX	0.29-1.06	0.035	0.035	0.10MIN	0.40MAX	0.40	0.15MAX	0.40	0.080	275MIN	485MIN	30.0	-
STANDARD SPECIFICATION OF SEAMLESS CARBON-MOLYBDENUM ALLOY-STEEL BOILER AND SUPER HEATER TUBES																
8	ASTM A209/T1	AS	0.10-0.20	0.30-0.80	0.025	0.025	0.10-0.50	-	-	0.44-0.65	-	-	205MIN	380MIN	30.0	-
9	ASTM A209/T1A		0.15-0.25	0.30-0.80	0.025	0.025	0.10-0.50	-	-	0.44-0.65	-	-	195MIN	365MIN	30.0	-
10	ASTM A209/Tb		0.14MAX	0.30-0.80	0.025	0.025	0.10-0.50	-	-	0.44-0.65	-	-	220MIN	415MIN	30.0	-
STANDARD SPECIFICATION OF CARBON STEEL BOILER AND SUPER HEATER TUBES																
11	ASTM A210/A1	CS	0.27MAX	0.93MAX	0.035	0.035	0.10MIN	-	-	-	-	255MIN	415MIN	30.0	-	
12	ASTM A210/C		0.35MAX	0.29-1.06	0.035	0.035	0.10MIN	-	-	-	-	275MIN	485MIN	30.0	-	
STANDARD SPECIFICATION OF CARBON STEEL BOILER AND SUPER HEATER TUBES																
13	ASTM A213/T2	AS	0.10-0.20	0.30-0.60	0.025	0.025	0.10-0.30	0.50-0.81	-	0.44-0.65	-	-	205MIN	415MIN	30.0	-
14	ASTM A213/T5		0.15MAX	0.30-0.60	0.025	0.025	0.50MAX	4.00-6.00	-	0.45-0.65	-	-	205MIN	415MIN	30.0	-
15	ASTM A213/T11		0.05-0.15	0.30-0.60	0.025	0.025	0.50-1.00	1.00-1.50	-	0.44-0.65	-	-	205MIN	415MIN	30.0	-
16	ASTM A213/T12		0.05-0.15	0.30-0.61	0.025	0.025	0.50MAX	0.80-1.25	-	0.44-0.65	-	-	205MIN	415MIN	30.0	-
17	ASTM A213/T22		0.05-0.15	0.30-0.60	0.025	0.025	0.50MAX	1.90-2.60	-	0.87-1.13	-	-	205MIN	415MIN	30.0	-

Carbon and Alloy Seamless Steel Pipe Stock Is 20000T Perennially
 Focus On Carbon And Alloy Seamless Steel Pipe For 30 Years
www.sanonpipe.com

SPECIFICATION CHART OF TUBES AND PIPES																
CHEMICAL COMPOSITION													MECHANICAL PROPERTIES			
CS :- Carbon Steel													AS :- Alloy Steel			
													YIELD STRESS	TENSILE STRENGTH	ELONGATION IN	IMPACT TEST
SPECIFICATION	TYPE	C %	Mn%	P % MAX	S% MAX	Si %	Cr %	Cu % MAX	Mo % MAX	Ni % MAX	Va&	MPa	MPa	50mmMIN Longitudinal	-50°1 40x10	
23	ASTM A335/P2		0.10-0.20	0.30-0.61	0.025	0.025	0.10-0.30	0.50-0.81	-	0.44-0.65	-	-	205MIN	380MIN	30.0	-
24	ASTM A335/P5		0.15MAX	0.30-0.60	0.025	0.025	0.50MAX	4.00-6.00	-	0.45-0.65	-	-	205MIN	415MIN	30.0	-
25	ASTM A335/P11		0.05-0.15	0.30-0.60	0.025	0.025	0.50-1.00	1.00-1.50	-	0.44-0.65	-	-	205MIN	415MIN	30.0	-
26	ASTM A335/P12		0.05-0.15	0.30-0.60	0.025	0.025	0.50MAX	0.80-1.25	-	0.44-0.65	-	-	220MIN	415MIN	30.0	-
27	ASTM A335/P22		0.05-0.15	0.30-0.60	0.025	0.025	0.50MAX	1.90-2.60	-	0.87-1.13	-	-	205MIN	415MIN	30.0	-
STANDARD SPECIFICATION OF CARBON STEEL BOILER AND SUPER HEATER																
28	BS/3059 /1/ 320	CS	0.16MAX	0.30-0.70	0.050	0.050	-	-	-	-	-	-	195MIN	320-480	25.0	-
29	BS/3059 /2/ 360	CS	0.17MAX	0.40-0.80	0.045	0.045	0.35MAX	-	-	-	-	-	215MIN	360-500	24.0	-
30	BS/3059 / 440	CS	0.12-0.18	0.90-1.20	0.040	0.035	0.10-0.35	-	-	-	-	-	245MIN	440-560	21.0	-
32	BS/3059/2/ 620	AS	0.12-0.15	0.40-0.70	0.040	0.040	0.10-0.35	0.70-1.10	-	0.45-0.65	-	-	180 MIN	460-640	22.0	-
31	BS/3059/2/ 622	AS	0.08-0.15	0.40-0.70	0.040	0.040	0.10-0.35	2.00-2.50	-	0.90-1.20	-	-	275MIN	490-640	20.0	-
STANDARD SPECIFICATION FOR SEAMLESS ALLOY STEEL TUBES FOR BOILER, PIPELINES, PRESSURE VESSEL FOR TEMPRATURE UP TO 6000C																
33	DIN/17175 ST35.8	CS	0.17MAX	0.40-0.80	0.040	0.040	0.10-0.35	-	-	-	-	-	235MIN	340-441	25.0	-
34	DIN/17175 ST45.8	CS	0.21 MAX	0.40-1.20	0.040	0.040	0.10-0.35	-	-	-	-	-	235MIN	441-540	25.0	-
35	DIN/17175 15M03	AS	0.12-0.20	0.40-0.80	0.035	0.035	0.10-0.35	-	-	0.25-0.35	-	-	285MIN	441-540	21.0	-
36	DIN/17175 13CM044	AS	0.10-0.18	0.40-0.70	0.035	0.035	0.10-0.35	0.70-1.00	-	0.45-0.65	-	-	294MIN	441-570	22.0	-
36	DIN/17175 10CrMo910	AS	0.15MAX	0.40-0.80	0.035	0.035	0.10-0.35	2.00-2.50	-	0.90-1.10	-	-	265MIN	441-590	20.0	-
STANDARD SPECIFICATION FOR SEAMLESS CARBON STEEL TUBES																
37	JIS3445 STKM 11A		0.12MAX	0.60MAX	0.040	0.040	0.35MAX	-	-	-	-	-	-	294MIN	35.0	-
38	JIS3445 STKM 12A		0.20MAX	0.60MAX	0.040	0.040	0.35MAX	-	-	-	-	-	177MIN	344MIN	35.0	-

Carbon and Alloy Seamless Steel Pipe Stock Is 20000T Perennially
 Focus On Carbon And Alloy Seamless Steel Pipe For 30 Years
www.sanonpipe.com

SPECIFICATION CHART OF TUBES AND PIPES																	
CHEMICAL COMPOSITION													MECHANICAL PROPERTIES				
CS :- Carbon Steel													AS :- Alloy Steel				
													YIELD STRESS	TENSILE STRENGTH	ELONGATION IN	IMPACT TEST	
SPECIFICATION	TYPE	C %	Mn%	P % MAX	S% MAX	Si %	Cr %	Cu % MAX	Mo % MAX	Ni % MAX	Va&	MPa	MPa	50mmMIN Longitudinal	-50°1 40x10		
39	JIS3445 STKM 12B	CS	0.20MAX	0.60MAX	0.040	0.040	0.35MAX	-	-	-	-	-	274MIN	393MIN	25.0	-	
40	JIS3445 STKM 12C		0.20MAX	0.60MAX	0.040	0.040	0.35MAX	-	-	-	-	-	353MIN	470MIN	20.0	-	
41	JIS3445 STKM 13C		0.25MAX	0.30MAX	0.040	0.040	0.35MAX	-	-	-	-	-	216MIN	373MIN	30.0	-	
42	JIS3445 STKM 13B		0.25MAX	0.30-0.90	0.040	0.040	0.35MAX	-	-	-	-	-	304MIN	442MIN	20.0	-	
43	JIS 3461 STB42		0.32MAX	0.30-0.80	0.035	0.035	0.35MAX	-	-	-	-	-	255MIN	412MIN	30.0	-	
44	JIS 3461 STB35		0.18MAX	0.30-0.60	0.035	0.035	0.35MAX	-	-	-	-	-	177MIN	344MIN	30.0	-	
45	ASTM A 519 SAE 1010	CS	0.08-0.13	0.30-0.60	0.040	0.050	-	-	-	-	-	-				-	
46	ASTM A 519 SAE 1015		0.13-0.18	0.30-0.60	0.040	0.050	-	-	-	-	-	-				-	
47	ASTM A 519 SAE 1020		0.18-0.23	0.30-0.60	0.040	0.050	-	-	-	-	-	-				-	
48	ASTM A 519 SAE 1025	CS	0.22-0.28	0.30-0.60	0.040	0.050	-	-	-	-	-	-				-	
49	ASTM A 519 SAE 1030		0.28-0.34	0.60-0.90	0.040	0.050	-	-	-	-	-	-				-	
50	ASTM A 519 SAE 1035		0.32-0.38	0.60-0.90	0.040	0.050	-	-	-	-	-	-				-	
51	ASTM A 519 SAE 1040		0.37-0.44	0.60-0.90	0.040	0.050	-	-	-	-	-	-				-	
52	ASTM A 519 SAE 1045		0.43-0.50	0.60-0.90	0.040	0.050	-	-	-	-	-	-				-	
53	ASTM A 519 SAE 1050		0.48-0.55	0.60-0.90	0.040	0.050	-	-	-	-	-	-				-	

Carbon and Alloy Seamless Steel Pipe Stock Is 20000T Perennially
 Focus On Carbon And Alloy Seamless Steel Pipe For 30 Years
www.sanonpipe.com